



Net.Fluid



General Information: Compatibility



Allgemeine Informationen: Kompatibilität



Informations Générales: Compatibilité



Informaciones de Carácter General: Compatibilidad



Informazioni Generali: Compatibilità

Very Good

Good

Not indicated

Absolutely No-Good

No - Tested

Standard fluids 20°C or indicated

Compatibility - Kompatibilität - Compatibilité - Compatibilidad - Compatibilità

Media	316L	Brass	FKM	P.T.F.E.	Media	316L	Brass	FKM	P.T.F.E.
Acetaldeidhyde	Green	Red	Yellow	Green	Butadiene	Green	Yellow	Yellow	Green
Acetic acid	Green	Yellow	Red	Green	Butane	Blue	Green	Blue	Green
Acetic anydride	Blue	Yellow	Red	Green	Butyl alcohol	Green	Blue	Green	Green
Acetic solvents	Green	Green	Red	Green	Butylene	Green	Green	Red	Green
Acetone	Green	Green	Red	Green	Butyric acid	Blue	Yellow	Yellow	Green
Acetylene	Green	Yellow	Green	Green	Calcium bisulphate	Blue	Blue	Green	Green
Acrylonitrile	Green	Green	Yellow	Green	Calcium carbonate	Blue	Yellow	Green	Green
Air	Green	Green	Green	Green	Calcium chlorite	Blue	Blue	Green	Green
Alum	Green	Yellow	Green	Green	Calcium hypochlorite	Yellow	Red	Blue	Green
Aluminium chloride - Dry	Green	Blue	Green	Green	Calcium sulphate	Blue	Yellow	Green	Green
Aluminium sulphate	Green	Yellow	Green	Green	Carbon dioxide CO2	Green	Green	Blue	Green
Ammonia solution	Green	Red	White	Green	Carbon sulphide	Blue	Yellow	Green	Green
Ammonium bicarbonate	Blue	Blue	Green	Green	Carbon tetrachloride (dry)	Green	Yellow	Blue	Green
Ammonium carbonate	Blue	Blue	Blue	Green	Carbon tetrachloride (wet)	Blue	Red	Blue	Green
Ammonium chloride	Yellow	Red	Green	Green	Carbonated water	Green	Blue	Green	Green
Ammonium monophosphate	Blue	Red	Green	Green	Carbonic acid	Blue	Red	Green	Green
Ammonium nitrate	Green	Red	Green	Green	Castor oil	Green	Green	Green	Green
Ammonium phosphate - Dibasic	Blue	Yellow	Green	Green	Chlorinated solvents (dry)	Blue	Yellow	Yellow	Green
Ammonium phosphate - Tribasic	Blue	Yellow	Green	Green	Chlorine (wet)	Red	Red	White	Green
Ammonium sulphate	Blue	Blue	Green	Green	Chloro - gas (dry)	Blue	Yellow	Blue	Green
Amyl acetate	Blue	Blue	Red	Green	Chloroacetic acid	Red	Yellow	Yellow	Green
Amyl alcohol	Green	Blue	Green	Green	Chlorobenzene (dry)	Green	Blue	Green	Green
Anhydrous ammonia	Green	Red	Blue	Green	Chloroform (dry)	Green	Blue	Blue	Green
Anhydrous nitric acid	Green	Red	Red	Green	Chlorosulphonic acid (dry)	Blue	Blue	White	Green
Aniline	Blue	Yellow	Yellow	Green	Chlorosulphonic acid (wet)	Red	Red	White	Green
Aniline - colouring	Green	Yellow	Blue	Green	Chrome alum	Green	Yellow	White	Green
Animal oil	Green	Green	Blue	Green	Chromic acid	Yellow	Red	Yellow	Green
Antimony trichlore	Red	Red	Yellow	Green	Coconut oil	Blue	Blue	Green	Green
Arsenic Acid	Blue	Red	Green	Green	Cokeoven gas	Green	Yellow	Blue	Green
Asphalt	Green	Green	Blue	Green	Cooling oil	Green	Blue	Green	Green
Barium hydroxide	Blue	Blue	Green	Green	Copper acetate	Green	Red	White	Green
Barium sulphate	Blue	Yellow	Green	Green	Copper chloride	Yellow	Red	Green	Green
Beer	Green	Green	Green	Green	Copper nitrate	Blue	Red	Green	Green
Benzaldehyde	Green	Green	Red	Green	Corn oil	Blue	Blue	Green	Green
Benzoic acid	Blue	Blue	Green	Green	Cottonseed oil	Blue	Blue	Green	Green
Benzol-Benzene	Blue	Blue	Red	Green	Creosote oil	Blue	Blue	Green	Green
Borax	Blue	Green	Green	Green	Cresylic acid	Blue	Yellow	Blue	Green
Boric Acid	Blue	Blue	Green	Green	Crude oil (sour)	Green	Yellow	Green	Green
Brine	Blue	Blue	Green	Green	Crude oil (sweet)	Green	Blue	Green	Green
Bromine - Dry	Red	Green	Red	Green	Cupric sulphate	Blue	Red	Green	Green
Bromine - Wet	Red	Blue	Red	Green	Cyclohexane	Green	Green	Green	Green



Net.Fluid



General Information: Compatibility

Very Good



Allgemeine Informationen: Kompatibilität

Good



Informations Générales: Compatibilité

Not indicated



Informaciones de Carácter General: Compatibilidad

Absolutely No-Good



Informazioni Generali: Compatibilità

No - Tested

Standard fluids 20°C or indicated

Compatibility - Kompatibilität - Compatibilité - Compatibilidad - Compatibilità

Media	316L	Brass	FKM	P.T.F.E.	Media	316L	Brass	FKM	P.T.F.E.
Diethylamide	Green	Green	White	Green	Hydrobromic acid	Red	Red	White	Green
Distilled water (aerated)	Green	Green	Green	Green	Hydrobromic acid (aerated)	Red	Red	White	Green
Drying oil	Blue	Yellow	White	Green	Hydrocyanic acid	Green	Red	White	Green
Edible vegetable oil	Green	Blue	Green	Green	Hydrofluoric acid	Red	Red	White	White
Epsom salt	Blue	Blue	Green	Green	Hydrofluosillicic acid	Yellow	Green	White	Green
Ethane	Blue	Green	Green	Green	Hydrogen peroxide (concentrated)	Blue	Red	White	Green
Ethers	Green	Blue	Yellow	White	Hydrogen peroxide (diluted)	Blue	Blue	Green	Green
Ethyl acetate	Blue	Yellow	Red	Green	Hydrogen sulphide (dry)	Green	Yellow	Green	Green
Ethyl acrylate	Green	Blue	Red	Green	Hydrogen sulphide (wet)	Blue	Red	Green	Green
Ethyl alcohol	Blue	Blue	Green	Green	Ink	Green	Yellow	Green	Green
Ethyl chloride (dry)	Green	Blue	White	Green	Iodine (wet)	Red	Red	White	Green
Ethyl chloride (wet)	Blue	Yellow	White	Green	Iodoform	Green	Yellow	Green	Green
Ethylen glycol	Blue	Blue	Green	Green	Isoctane	Green	Green	Green	Green
Ethylene oxide	Blue	Green	Red	Green	Isopropyl alcohol	Blue	Blue	Green	Green
Ethylene perchlorine (dry)	Green	Yellow	Green	Green	Isopropyl ether	Green	Green	White	Green
Ferric nitrate	Yellow	Red	Green	Green	Jelly	Green	Green	Green	Green
Ferric sulphate	Blue	Red	Green	Green	Kerosene	Green	Green	Green	Green
Ferrous chloride	Red	Red	Green	Green	Ketone	Green	Green	Red	Green
Ferrous sulphate	Blue	Blue	Green	Green	Lacquers (and solvents)	Green	Green	Red	Green
Ferrous sulphate (saturated)	Green	Yellow	White	Green	Lactic acid	Green	Red	White	Green
Fertilizer solutions	Blue	Yellow	Green	Green	Lead acetate	Blue	Yellow	Green	Green
Fish oil	Green	Blue	Green	Green	Lemon juice	Blue	Blue	Green	Green
Fluorine (dry)	Red	Red	White	Green	Lighting gas	Green	Green	Green	Green
Formaldehyde (cold)	Green	Green	Green	Green	Linolenic acid	Green	Blue	Green	Green
Formaldehyde (hot)	Yellow	Blue	White	Green	Linseed oil	Blue	Blue	Green	Green
Formic acid (cold)	Blue	Blue	Green	Green	Liquid gas (LPG)	Blue	Green	Green	Green
Formic acid (hot)	Blue	Blue	Green	Green	Liquor ammonia	Green	Red	Green	Green
Freon (dry)	Green	Blue	Yellow	Green	Lubricating oil	Green	Blue	Green	Green
Fruit juices	Green	Blue	Green	Green	Magnesium bisulphate	Green	Blue	White	Green
Fuel oil	Green	Blue	Green	Green	Magnesium chloride	Blue	Blue	Green	Green
Furfural	Green	Green	Red	Green	Magnesium sulphate	Blue	Blue	Green	Green
G.A. solvents	Green	Green	White	Green	Maleic acid	Blue	Blue	Green	Green
Gallic acid	Blue	Yellow	White	Green	Malic acid	Blue	Blue	Green	Green
Gas hydrogen (cold)	Green	Blue	White	Green	Mercuric chloride	Yellow	Red	White	Green
Glucose	Green	Green	Green	Green	Mercuric cyanide	Green	Red	White	Green
Glue	Blue	Blue	Green	Green	Mercury	Green	Red	Green	Green
Glycerin	Green	Blue	Green	Green	Methane	Blue	Green	Green	Green
Glycols	Blue	Blue	Green	Green	Methyl acetate	Green	Green	Red	Green
Heptane	Green	Blue	Green	Green	Methyl alcohol	Blue	Blue	Blue	Green
Hexane	Blue	Blue	Green	Green	Methyl chloride	Green	Green	White	Green
Hydraulic oil (petroleum base)	Green	Blue	Green	Green	Methyl ethyl ketone	Green	Green	Red	Green



Net.Fluid



General Information: Compatibility



Allgemeine Informationen: Kompatibilität



Informations Générales: Compatibilité



Informaciones de Carácter General: Compatibilidad



Informazioni Generali: Compatibilità

Very Good

Good

Not indicated

Absolutely No-Good

No - Tested

Standard fluids 20°C or indicated

Compatibility - Kompatibilität - Compatibilité - Compatibilidad - Compatibilità

Media	316L	Brass	FKM	P.T.F.E.	Media	316L	Brass	FKM	P.T.F.E.
Methyl formate	Good	Absolutely No-Good	No - Tested	Very Good	Phosphoric acid 50% (hot)	Absolutely No-Good	Absolutely No-Good	Very Good	Very Good
Methylamine	Very Good	Absolutely No-Good	No - Tested	Very Good	Phosphoric acid 85% (cold)	Very Good	Absolutely No-Good	No - Tested	Very Good
Methylene chloride	Very Good	Very Good	Not indicated	Very Good	Phosphoric acid 85% (hot)	Very Good	Absolutely No-Good	No - Tested	Very Good
Milk	Very Good	Very Good	Very Good	Very Good	Phtalic acid	Good	Good	Very Good	Very Good
Mineral oil	Very Good	Good	Very Good	Very Good	Phtalic anydride	Good	Good	Very Good	Very Good
Muds	Very Good	Good	Very Good	Very Good	Picric acid	Good	Good	No - Tested	Very Good
Muriatic acid	Absolutely No-Good	Absolutely No-Good	Very Good	Very Good	Pine oil	Very Good	Good	Very Good	Very Good
Naphta	Good	Good	Very Good	Very Good	Potassium bichromate	Good	Absolutely No-Good	Very Good	Very Good
Naphtalene	Good	Good	Very Good	Very Good	Potassium bisulphate	Good	Not indicated	Very Good	Very Good
Natural gas	Very Good	Good	Very Good	Very Good	Potassium bromide	Very Good	Not indicated	Very Good	Very Good
Nickel chloride	Good	Absolutely No-Good	Very Good	Very Good	Potassium carbonate	Good	Good	Very Good	Very Good
Nickel nitrate	Good	Absolutely No-Good	Very Good	Very Good	Potassium chlorate	Good	Good	Very Good	Very Good
Nickel sulphate	Good	Absolutely No-Good	Very Good	Very Good	Potassium chloride	Not indicated	Good	Very Good	Very Good
Nicotinic acid	Very Good	Very Good	No - Tested	Very Good	Potassium cyanide	Good	Absolutely No-Good	Very Good	Very Good
Niter cake 10%	Very Good	Good	Very Good	Very Good	Potassium diphosphate	Very Good	Good	Very Good	Very Good
Nitric acid 10%	Very Good	Absolutely No-Good	Very Good	Very Good	Potassium ferrocyanide	Good	Good	Very Good	Very Good
Nitric acid 30%	Very Good	Absolutely No-Good	Very Good	Very Good	Potassium iodide	Good	Absolutely No-Good	Very Good	Very Good
Nitric acid 80%	Very Good	Absolutely No-Good	Good	Very Good	Potassium nitrate	Good	Good	Very Good	Very Good
Nitric acid 100%	Very Good	Absolutely No-Good	Good	Very Good	Potassium permanganate	Good	Good	Very Good	Very Good
Nitrobenzene	Good	Absolutely No-Good	Not indicated	Very Good	Potassium sulphate	Good	Good	Very Good	Very Good
Nitrogen	Very Good	Very Good	Very Good	Very Good	Potassium sulphide	Very Good	Good	No - Tested	Very Good
Nitrogen oxide	Good	Absolutely No-Good	No - Tested	Very Good	Propane	Good	Very Good	Very Good	Very Good
Nitrous gas	Very Good	Absolutely No-Good	No - Tested	Very Good	Propyl alcohol	Very Good	Very Good	No - Tested	Very Good
Oil-water blend	Very Good	Very Good	Very Good	Very Good	Propylene glycol	Good	Good	Very Good	Very Good
Oleic acid	Good	Good	Very Good	Very Good	Pyrogallic acid	Good	Good	Very Good	Very Good
Oleum	Good	Very Good	Not indicated	Very Good	Resins	Very Good	Very Good	No - Tested	Very Good
Olive oil	Very Good	Good	Very Good	Very Good	Rubber latex emulsions	Very Good	Very Good	Very Good	Very Good
Oxalic acid	Good	Good	Very Good	Very Good	Rubber solvents	Very Good	Very Good	Absolutely No-Good	Very Good
Oxygen	Very Good	Very Good	No - Tested	Very Good	Salicylic acid	Very Good	Not indicated	Very Good	Very Good
Ozone (dry)	Very Good	Good	Very Good	Very Good	Seawater	Very Good	Good	Very Good	Very Good
Ozone (wet)	Very Good	Very Good	Very Good	Very Good	Shellac	Very Good	Very Good	No - Tested	Very Good
Palm oil	Good	Good	Very Good	Very Good	Silver nitrate	Good	Absolutely No-Good	Very Good	Very Good
Palmitic acid	Good	Good	Very Good	Very Good	Soap solutions (stearates)	Very Good	Very Good	Very Good	Very Good
Paraffin	Very Good	Very Good	Very Good	Very Good	Sodium acetate	Good	Good	Very Good	Very Good
Paraformaldehyde	Good	Good	No - Tested	Very Good	Sodium aluminate	Good	Good	Very Good	Very Good
Pentane	Very Good	Very Good	Very Good	Very Good	Sodium bicarbonate	Good	Good	Very Good	Very Good
Petrol	Very Good	Very Good	Very Good	Very Good	Sodium bisulphate 10%	Very Good	Good	Very Good	Very Good
Phenol	Good	Good	Good	Very Good	Sodium borate	Good	Good	Very Good	Very Good
Phosphoric acid 10% (cold)	Good	Absolutely No-Good	Very Good	Very Good	Sodium bromide 10%	Good	Good	Very Good	Very Good
Phosphoric acid 10% (hot)	Absolutely No-Good	Absolutely No-Good	Very Good	Very Good	Sodium carbonate	Good	Good	Very Good	Very Good
Phosphoric acid 50% (cold)	Good	Absolutely No-Good	Very Good	Very Good	Sodium chlorate	Good	Good	Very Good	Very Good



General Information: Compatibility

Very Good



Allgemeine Informationen: Kompatibilität

Good



Informations Générales: Compatibilité

Not indicated



Informaciones de Carácter General: Compatibilidad

Absolutely No-Good



Informazioni Generali: Compatibilità

No - Tested

Standard fluids 20°C or indicated

Compatibility - Kompatibilität - Compatibilité - Compatibilidad - Compatibilità

Media	316L	Brass	FKM	P.T.F.E.
Sodium chloride	Good	Good	Very Good	Very Good
Sodium chromate	Very Good	Not indicated	Very Good	Very Good
Sodium cyanide	Good	Absolutely No-Good	Very Good	Very Good
Sodium fluorine	Good	Not indicated	Very Good	Very Good
Sodium hydroxide (cold)	Very Good	Very Good	Good	Very Good
Sodium hydroxide (hot)	Very Good	Very Good	Not indicated	Very Good
Sodium hypochlorite	Not indicated	Absolutely No-Good	Very Good	Very Good
Sodium metaphosphate	Very Good	Not indicated	Very Good	Very Good
Sodium metasilicate (cold)	Very Good	Good	Very Good	Very Good
Sodium metasilicate (hot)	Very Good	Good	Very Good	Very Good
Sodium nitrate	Good	Good	Very Good	Very Good
Sodium perborate	Good	Good	Very Good	Very Good
Sodium peroxide	Good	Absolutely No-Good	Very Good	Very Good
Sodium phosphate (dibasic)	Good	Not indicated	Very Good	Very Good
Sodium phosphate (tribasic)	Good	Not indicated	Very Good	Very Good
Sodium silicate	Good	Good	Very Good	Very Good
Sodium silicate (hot)	Good	Not indicated	Very Good	Very Good
Sodium sulphate	Very Good	Good	Very Good	Very Good
Sodium sulphide	Good	Absolutely No-Good	Very Good	Very Good
Sodium sulphide (hot)	Good	Absolutely No-Good	Very Good	Very Good
Sodium thiosulphate	Very Good	Good	Very Good	Very Good
Soft water	Very Good	Very Good	Very Good	Very Good
Sour gasoline	Very Good	Good	Very Good	Very Good
Soybean oil	Very Good	Good	Very Good	Very Good
Stannous chloride	Not indicated	Absolutely No-Good	Very Good	Very Good
Starch	Good	Good	Very Good	Very Good
Stearic acid	Good	Not indicated	Very Good	Very Good
Styrene	Very Good	Very Good	Very Good	Very Good
Sulphur	Good	Absolutely No-Good	Very Good	Very Good
Sulphuric acid 0-7%	Good	Not indicated	Very Good	Very Good
Sulphuric acid 20%	Absolutely No-Good	Not indicated	Very Good	Very Good
Sulphuric acid 50%	Absolutely No-Good	Good	Very Good	Very Good
Sulphuric acid 100%	Very Good	Very Good	Good	Very Good
Sulphuric anhydride (dry)	Very Good	Good	Very Good	Very Good
Sulphurous anhydride (dry)	Very Good	Good	Very Good	Very Good
Synthesis gas	Good	Good	Very Good	Very Good
Tannic acid	Good	Good	Very Good	Very Good
Tar	Very Good	Very Good	Very Good	Very Good
Tartaric acid	Good	Very Good	Very Good	Very Good
Tetraethyl lead	Good	Good	Very Good	Very Good
Tin tetrachloride	Absolutely No-Good	Not indicated	Very Good	Very Good

Media	316L	Brass	FKM	P.T.F.E.
Toluol or toluene	Very Good	Very Good	Good	Very Good
Tomato juice	Very Good	Not indicated	Very Good	Very Good
Transformer oil	Very Good	Good	Very Good	Very Good
Tributyl phosphate	Very Good	Very Good	No - Tested	Very Good
Trichloroethylene	Good	Good	Good	Very Good
Turpentine	Good	Good	Very Good	Very Good
Urea	Good	Good	No - Tested	Very Good
Varnishes	Very Good	Very Good	No - Tested	Very Good
Vaseline	Good	Good	Very Good	Very Good
Vegetable oil	Very Good	Good	Very Good	Very Good
Vinegar	Very Good	Good	Absolutely No-Good	Very Good
Wax emulsions	Very Good	Very Good	Very Good	Very Good
Waxes	Very Good	Very Good	Very Good	Very Good
Wood oil	Very Good	Good	Very Good	Very Good
Xylene (dry)	Very Good	Very Good	Good	Very Good
Zinc chloride	Absolutely No-Good	Absolutely No-Good	Very Good	Very Good
Zinc hydrosulphite	Very Good	Not indicated	Very Good	Very Good
Zinc sulphate	Good	Good	Very Good	Very Good